



# Embedded PDV in Cast Explosives

PDV Workshop

September 8-9, 2010

Jason W. Podsednik



Sandia National Laboratories is a multi-program laboratory managed and operated by Sandia Corporation, a wholly owned subsidiary of Lockheed Martin Corporation, for the U.S. Department of Energy's National Nuclear Security Administration under contract DE-AC04-94AL85000.





## Motivations

- Develop and validate model simulations
- Gain as much knowledge about a “device” (in this case, a melted and cast material) found in the field by experimental means on the range.
- Previously used embedded diagnostics such as carbon resistor gauges, have been moderately successful. Why not try PDV?
- PDV seems to be a more “elegant” approach.





## Questions

- ?- Will the PDV and optical components survive the melt / pour temperature of Composition-B ( $\approx 80^{\circ}\text{C}$ )?
- ?- If we embedded fibers inside a cast material, and send a shock wave through the material, could we accurately measure it?
- ?- Because of the inherent voids left behind during the cooling process (TNT shrinkage of 12%), would we simply recover only very local conditions? Will the probes survive?
- ?- Will the difference in sound speeds in the various materials used in the experiment effect the PDV data?






# PDV Probe Considerations


## Mirrored fiber reflector vs. bare, cleaved fiber

Mirrored fiber reflector



With boot removed

Bare, Cleaved fiber



Would either of these probes survive the melt / pour temperature of composition-B (80°C)?




## PDV Thermal Test / Wax Test Shot

*Will the PDV Components even survive?*

PDV Probe in Boiling  
Water (100°C)



PDV Probe  
embedded in wax  
melted @  $\approx 70^\circ\text{C}$






# PDV Thermal Test / Wax Test Shot

*What kind of data will we get?*

PDV Probe



C12 Load with  
standard M16  
Detonator









# PDV Thermal Test / Wax Test Shot

*Expected velocity  $\approx 200$  m/sec*

Mirrored  
Probe Data





Cleaved  
Fiber Data





# Drum Instrumentation


*Experimental Measurements for Model Development/Validation*





# Drum Instrumentation

*PDV Probe Locations*




PDV Probe  
Locations





# Drum Instrumentation

*PDV probes alone just not enough!*



Aluminum housing

Thermocouples






# Drum Instrumentation

*A note on the finished product...not what we embedded PDV probes into!*

Melt cast explosive

Bummer!




NOTE: A single-stage pour does not yield a desirable finish





## Drum Instrumentation

*This IS what we embedded probes into!*



Much better!

NOTE: Day and Zimmerman Inc. have a MUCH higher quality explosive casting process.






# Test Set-up

*Non-detonation desired*

Test Drum



PDV Probe with TOAD pins



Water Disrupter Tool  
(1.4 km/sec insult)

Strain Gauge and  
thermocouple






# Test Set-up

*Non-detonation achieved!*

Test Drum



PDV Probes not destroyed!



Bare Fiber not broken!





# Shot Day

*“Clean-up” shot...not a good time for flying!*



9-2-10 real time clean up shot.asf







# PDV Data Results

*Front outside probes agree as wave travels around drum*


- Predicted TOA between front and rear probes 1.5 msec.
- Front probes impacted at 560  $\mu$ sec
- No “impact” seen by rear PDV; probe still attached to drum post-shot.



- Slow (<20 m/sec) drum wall movement noticed?
- Will this couple into the internal PDV measurements?



Insult









# PDV Data Results

## *Internal probes*

- Expected  $\approx 0.9$  msec to hit the first probes.
- PDV channels see faster “peaks” between 0.9 and 1.5 msec.

- LOTS of low velocity components.
- Sees first “data” at 61, 42, 42, and 57  $\mu$ sec respectively. Is this caused by the sound speed in steel coupling into fibers?





## Summary

- PDV diagnostics did survive the melt/pour process, and were embedded inside of a cast explosive (one small success).
- It is believed that the steel drum coupled vibration into the internal probes prior to “real” data. Any thoughts on how to isolate this effect?
- Data, while rather ambiguous, does exhibit “events” happening at the expected times.
- Has anyone else done anything like this before? Are we going about this process all wrong?

